

SOLUTIONS™ VINTAGE PUFF™



FEED MATERIAL
into plotter/cutter
so that the media
faces up.



PRINT DESIGN
in positive form.
(do not mirror)



CUT DESIGN
If cutting through
ink, let the print dry
for 2-4 hours;
otherwise you may
cut immediately.
Dry times may vary.




WEED
away the excess
media. If the print was
cut immediately,
the print must dry
30-60 minutes
before proceeding.



PLACE MASK
over the graphic,
making sure to
smooth out any air
bubbles.

REMOVE
backing revealing
material's adhesive.



PREHEAT & POSITION
Preheat garment for
10 seconds, prior to
application. Position the
graphic to be applied &
cover with Kraft Paper.



HEAT APPLY
Temperature:
325-330°F; 162-165°C
Time:
3-5 seconds
Pressure:
medium
#6 on Hotronix[®]



PEEL MASK HOT
Cover with Kraft Paper or
Teflon[®] Sheet and reseat
for 13-15 seconds.

Description

For use with solvent and eco solvent print and cut systems. Solutions™ Vintage Puff™ is perfect for creating unique designs and graphics with a raised appearance.
(PU, 125 micron [+/-10%])

Recommended Fabrics

100% cotton
100% polyester
Poly/cotton blends
Lykra[®]/ Spandex blends
Woven nylon
Nylon knits
Nylon meshes - micro, tricot,
mini, reversible
Polyester knits
Polyester mesh
Poly/foam & cotton caps
Satin
Cordura[®]

Due to the combination of fabrics, weaves, and dyes used in the textile industry, Stahls' recommends and provides samples of our materials and medias for testing.

Accessories Required

CAD-COLOR[®] Solutions™ Mask
Kraft Paper/Teflon[®] Sheet
EZ Weeder[®] or Tweezers

Cutting Notes

Be sure to perform test cuts to ensure proper blade depth when cutting. Cutting too deep will result in weeding or masking difficulties.

Care Instructions

For best results, turn the garment inside out. Machine wash warm or cold using mild detergent. Do not use bleach. Do not iron directly on transfer. Tumble dry at low setting. Do not dry-clean. Natural distressing can occur with repeated washings.

Storage

Store in cool, dry area. Avoid direct heat, sunlight and humidity..

CUTTER GUIDELINES

CUTTER	BLADE	FORCE	OFFSET	SPEED
Roland SP-300	45°	90g	.25	30cm/s
Roland VP-300	45°	125g	0	30cm/s
Roland XC-540	45°	105g	.15	30cm/s
Roland GX-24	45°	100g	.225	30cm/s
Mimaki CG-75 FX	SPB-0001	100g	.10	50cm/s

All technical information and recommendations are based on tests we believe to be reliable. However, we cannot guarantee performance for conditions not under manufacturer's control. Before using, please determine the suitability of product for its intended use. The user assumes all risk and liability whatsoever in connection with the use of this product. Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective by manufacturer.

CAD-CUT, CAD-LAB, Pressure Sensitive Poly-TWILL, & Hotronix are trademarks & ® trademarks of GroupeSTAHL™ with one or more patents or patents pending.
© Stahls' International™ 2009 - All International Rights Reserved